

Epifanes Woodfinish Matte

One component matte varnish with UV filter



PRODUCT DESCRIPTION

Epifanes Woodfinish Matte is a fast drying, scratch resistant one component varnish based on urethane alkyd resins. This varnish gives a beautiful matte finish. It gives great protection against alcohol and other household chemicals. It can be used in an interior system or an exterior system.

Field of use: As a matte final coat in a new system or as a maintenance varnish in an existing system. It can be applied on basically every varnish. For bare wood we always recommend to start with build up coats of high gloss varnish with UV filter. This is to protect the wood from the inside of the grain.

PRODUCT INFORMATION

Type	Oxidative drying
Base	Urethane alkyd resin
Gloss	Matte
Colour	Transparent amber
Density at 20°C.	0,928 g/cm ³
Viscosity	30 seconds ISO-cup 6 mm
Solids Contents	45 ± 2 vol. %
VOC-level	473 g/l
Packing	1000ml.
Shelf life	3 years in closed unopened container stored in a dry location at temperatures between 5 - 30°C
Rec. filmthickness	70 µm wet = 30 µm dry
Thinner brush	Epifanes Brushthinner for Paint & Varnish or a good quality white spirit
Thinner spray	Epifanes Spraythinner for Paint & Varnish or denaturated alcohol
Thinning in general	Thinning ratio depends on temperature of product and working area. Avoid overthinning. For thinning ratios, see the Epifanes varnish system

Drying times	10°C.	15°C.	20°C.	25°C.
Dust dry	3 hours	2 hours	1 hours	45 minutes
Sandable	24 hours	18 hours	12 hours	10 hours
Recoatible	24 hours	18 hours	12 hours	10 hours

The above mentioned drying times are indicative at 65% RAH and 30 µm dry filmthickness. Drying also depends on ventilation and applied wet filmthickness. Higher wet filmthickness and/or poor ventilation will result in longer drying times. Especially horizontal parts may take longer to dry due to high wet filmthickness. Allow each varnish coat sufficient time to dry. Do not apply wet-on-wet.

Substrate New system: Clean the previously applied high gloss varnish. Sand the coat with P240. Apply the Epifanes Woodfinish Matte in 2 coats.

Existing system: Clean the varnish and sand it with P240. Apply 2 coats of Woodfinish Matte where the 1st coat is lightly thinned to get in to the sanding scratches of the old varnish.



Epifanes Woodfinish Matte

One component Matte varnish for with UV filter

APPLICATION

Conditions during application	Temperature	minimal 8°C. - maximal 30°C.
	Relative air humidity	minimal 50% - maximal 85%

Best results are achieved by using a longhaired soft brush or by air spray. Because of the required wetfilmthickness application by roller is not advised. Evenly distribute the varnish over the surface and tip off along the wood grain. Avoid retipping. Do not apply wet-on-wet. Do not apply excessive wet films to avoid the formation of curtains and drying problems. Avoid varnishing in direct sunlight or much wind. A rapid loss of solvents will occur under these circumstances and this will decrease the flow. Avoid large difference in temperature of the product, surface to be varnish and working area. In case the product "pulls" and is difficult to apply, 10% thinner may be added. To retrieve the original colour of the wood, up to 10% Epifanes Mahogany Stain or Epifanes Teak Stain may be added to the varnish. After drying, lightly sand the surface with P400 or Scotch Brite. Always sand by hand along the wood grain.

Guidelines for spray application:

Thinning volume	Nozzle	Pressure	Visco DIN-cup 4 mm
10-15%	1.5 mm - 1.8 mm	2-3 Bar	20-24 sec.

SYSTEM BUILD UP (For exterior use)

Product	Step 1 EPIFANES Woodfinish Gloss	Step 2 EPIFANES Woodfinish gloss	Step 3 EPIFANES Woodfinish Matte
Numb. of coats	1	3-4	1-2
Thinner	EPIFANES Brushthinner PV	EPIFANES Brushthinner PV	EPIFANES Brushthinner PV
Thinning ratio	25-35%	0-10%	0-5%
Drying time 20°C.	24 hours	24 hours	12 hours
Sanding grit	Dry P220 - sand by hand	If subsequent coat is applied within 72 hours, sanding is not needed. For a smoother finish, lightly sand with P400 or Scotch Bright. After 72 hours always sand with P280-320	Wet P400 by hand or Scotch Bright.
Remarks	First penetrating varnish coat. For full varnish penetration into the wood fibers, apply this first coat heavily thinned.	The more coats of Woodfinish Gloss will provide more varnish depth.	These coats give the system a Matte finish. Always lightly sand between these final coats for finest result.

Theoretical coverage Practicle coverage

14m² per liter @ 30 µm dry filmthickness
Dependent on condition of substrate, loss of material due to factors such as application technique, shape of object, circumstances during application.

Recoatbility with other Epifanes varnishes

Epifanes Clear Varnish	High gloss alternative
Epifanes Woodfinish Gloss	High gloss alternative
Epifanes Rubbed Effect Varnish	Satin finish for interior
Epifanes Aqua Marine Interior Varnish	Water based satin finish fpr interior use
Epifanes Rapidcoat / Rapidclear	Semi gloss alternatief

Safety

The user of this product should obey all national laws and legislation concerning health, safety and environmental hazard. For more information on health and safety, we refer to the Material Safety Data Sheet of this product.

Although the facts and suggestions in this product information sheet are based on our own research and field experiences and are believed reliable, we cannot simply be held responsible for performance or results obtained through the use of this product. Ineffectiveness or other unintended consequences may result, because of such factors as weather, conditions, presence or other materials or the manner of preparation, use or application all of which are beyond W. Heeren & Zoon's control. All such risks are assumed by user.

DISCLAIMER OF WARRANTIES. Seller makes no express warranties. THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. In the event a warranty is created by law, buyer's EXCLUSIVE REMEDY shall be the replacement of any defective product. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or any other incidental or consequential loss) shall be available to buyer.

W. Heeren & Zoon BV
Oosteinderweg 32
1432 AL Aalsmeer
Netherlands
Phone +31 297 – 360366
info@epifanes.nl
www.epifanes.nl

EPIFANES®
Yacht Coatings